



**Spray Polyurethane Foam (SPF)
and
Cathedral Roofs & Cathedralized Attics**

To order copies of this publication, call 800-523-6154 and request SPFA Stock Number AY-141

Spray Polyurethane Foam Alliance
Copyright January 2003

RECOMMENDED
DESIGN CONSIDERATIONS
AND GUIDE SPECIFICATIONS

BUILDING ENVELOPE COMMITTEE (BEC)
Mission Statement

To provide a technical basis for expanding the use of polyurethane-foam-in-place within the building envelope.

To achieve this mission, the BEC will review and support the development of methods for performance evaluation of SPF, participate in activities leading to development, documentation and dissemination of information on applications of SPF in different building envelopes and systems.

To participate in the planning, organizing, documenting and supporting of construction and monitoring of selected demonstration projects with SPF in the building envelope.

To assist the Management and IPC committees in developing and carrying out market oriented programs.

BUILDING ENVELOPE COMMITTEE MEMBERS

Neal Ganser, Chairman
Corbond Corporation

Bill Amend
Foam Enterprises, Inc.

Robert Braun
The Dow Chemical Company

John Courier
Equipment & Coatings Technology

Tom Harris
BASF

Roger Morrison
NCFI

Mary Ellen Mueller
Convenience Products

Tom Shackelford
Pecora Corporation

John Stahl
Preferred Solutions, Inc.

Ad Hoc Members

Laverne Dagleish
CUFCA

Mort Sherman
consultMORT, Inc.

Anthony Woods
Can-Am Bld. Env. Specialists

This brochure was developed to aid specifiers in choosing spray-applied polyurethane foam systems. The information provided herein, based on current customs and practices of the trade, is offered in good faith and believed to be true, but is made WITHOUT WARRANTY, EITHER EXPRESS OR IMPLIED, AS TO FITNESS, MERCHANTABILITY, OR ANY OTHER MATTER. SPFA DISCLAIMS ALL LIABILITY FOR ANY LOSS OR DAMAGE ARISING OUT OF ITS USE. Individual manufacturers and contractors should be consulted for specific information. Nominal values which may be provided herein are believed to be representative, but are not to be used as specifications nor assumed to be identical to finished products. SPFA does not endorse the proprietary products or processes of any individual manufacturer, or the services of any individual contractor.

Spray Polyurethane Foam (SPF) And Cathedral Roofs & Cathedralized Attics

Closed cell, spray polyurethane foam (SPF) may be used to construct unvented cathedral roofs and cathedralized attics. It can be applied in sufficient thickness to satisfy local energy code requirements, directly to the underside of roof sheathing between rafters or joists of any slope in all (heating, mixed and cooling) climates.

This configuration controls the entry of moisture-laden air into the insulation and also eliminates dew-point occurring at the underside of the roof deck and anywhere in the insulation, in all (heating, mixed or cooling) climates*. Due to the fully adhered, closed cell properties of SPF, air and moisture are displaced out of the insulated space – including at rafters and sheathing. Moisture cannot enter the insulated space from any direction, eliminating the requirement for roof venting.

Venting above the closed cell SPF could reintroduce moisture laden air into a new air space below the roof sheathing, which may introduce another moisture condensation problem. Therefore, venting above the SPF in these configurations is not recommended.

*(Assumes the suitable thickness of SPF is applied to prevent condensation)

Spray Polyurethane Foam Alliance

4400 Fair Lakes Ct. Suite 105

Fairfax, VA 22033

800-523-6154

www.sprayfoam.org

CATHEDRAL ROOF DETAIL



